

FLOOR FINISH BASED ON **MEGATRAN[®] 205**

Formulation F-20-049-01 @ 25% N.V.

The **Megatran 205** polymer provides a high gloss finish that has excellent stress recoat resistance and excellent formulation latitude. This formulation is suitable for a maintenance environment where excellent gloss is desired with periodic burnishing.

Mix in Order Listed:

	<u>Weight %</u>
Water	30.60
Bactericide	Q.S.
Premixed Plasticizers:	
Tributoxyethyl Phosphate	2.40
Diethylene Glycol Ethyl Ether (low gravity)	4.50
1% Active Zonyl FSA	1.10
Dipropylene Glycol Methyl Ether	2.30
Megatran[®] 205 @ 38% N.V.	52.30
Syntran[®] PA-1445 @ 40% N.V.	2.80
Syntran[®] 6150 @ 40% N.V.	4.00
Defoamer	Q.S.
	100.00%

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 88 / 0 / 12