

Floor Finish based on **SYNTRAN 1284**

Formulation F-14-046-17

100 Gallon Formula @ 25% N.V.

Mix in Order Listed:

Water	268.6 Pounds
Bactericide	Q.S.
Premixed Plasticizers:	
Tributoxyethyl Phosphate	18.3
Diethylene Glycol Ethyl Ether – Low Gravity	45.9
1% Active Zonyl FSA	6.6
Ethylene Glycol Phenyl Ether	5.2
Syntran® 1284 @ 38% N.V.	460.3
Syntran® PA-1465 @ 38% N.V.	20.7
Syntran® 6150 W/E @ 40% N.V.	34.4
Defoamer	Q.S.
	<u>YIELD: 860.0</u>

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 89 / 0 / 4:7

8/04