

## FLOOR FINISH BASED ON **SYNTRAN MT<sup>®</sup> 233**

Formulation F-20-079-01 @ 33% N.V.

The **Syntran MT 233** formulation provides a unique application appearance enabling applicators to determine where finish is wet. This **Syntran MT 233** formulation is a high solids, durable formulation with low viscosity providing excellent leveling and flow out. This formulation is designed for dry brite maintenance environments and durable enough to be repaired with UHS burnishing using a medium or more aggressive pad. This formulation may also be incorporated as the coating of a scrub and recoat maintenance program.

*Mix in Order Listed:*

- 1) Charge vessel with **Syntran MT 233**.

**Weight %**

**Syntran MT 233 @ 40% N.V.**

66.70

- 2) Prepare premix in a separate vessel.

<i>Premix :</i>	
Water	12.40
Tributoxyethyl Phosphate	3.40
Diethylene Glycol Ethyl Ether – Low gravity	8.90
1% Active Zonyl FSA	1.20
Add defoamer allow to mix 30 minutes	
Defoamer	Q.S.

- 3) Slowly add premix to polymer at a rate of 4 gals / minute (rate for 100 gallon batch).

- 4) Allow premix and polymer to mix for ~30 minutes

- 5) Add waxes.

**Syntran<sup>®</sup> 6150 @ 40% N.V.**

5.20

**Syntran<sup>®</sup> PA-1445 @ 40% N.V.**

2.20

- 6) Mix for 30 minutes after wax addition.

- 7) Add bactericide allow to mix for 30 minutes.

Bactericide

Q.S.

100.00%

Adjust pH to 8.6 ± 0.2

Polvmer/Resin/Wax Ratio: 90 / 0 / 10

**FLOOR**