

APE FREE FLOOR FINISH BASED ON SYNTRAN® 6160

Formulation F-20-019-05. @ 22% N.V.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	332.40	38.50
Premix:		
Tributoxy Ethyl Phosphate	20.30	2.40
Diethylene Glycol Ethyl Ether	30.40	3.50
1% Active Zonyl FSN	6.80	0.80
Texanol	5.60	0.70
Dipropylene Glycol Methyl Ether	11.30	1.30
Syntran® 1905 @ 38% N.V.	373.20	43.40
Syntran® 6160 @ 35% N.V.	38.60	4.50
Syntran® PA-1445 @ 40% N.V.	21.10	2.50
Syntran® 1560 @ 25% N.V.	20.30	2.40
YIELD:	<u>860.00</u>	<u>100.00%</u>

Polymer/Resin/Wax Ratio: 84 / 3 / 13