

Interpolymer offers Syntran MT 220
in both **Gloss** and **Matte** finishes.

The formulation for Syntran MT 220 **Gloss**
is located on page 2 of this document.

The formulation for Syntran MT 220 **Matte**
is located on page 3 of this document.

FLOOR FINISH BASED ON **SYNTRAN MT[®] 220**

Formulation F-20-087-01 @ 21% N.V.

Mix in Order Listed:

	<u>Pounds</u>
Water	379.10
Bactericide	Q.S.
Premixed Plasticizers:	
Tributoxy Ethyl Phosphate	18.40
Diethylene Glycol Ethyl Ether (low gravity)	29.20
1% Active Zonyl FSJ	5.40
Ethylene Glycol Phenyl Ether	3.20
Syntran MT[®] 220 @ 38% N.V.	366.90
Syntran[®] 6150 W/E @ 40% N.V.	36.50
Syntran[®] PA-1465 @ 38% N.V.	21.30
Defoamer	Q.S.
YIELD:	860.00

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 86 / 0 / 14

6/04

MATTE FLOOR FINISH BASED ON **SYNTRAN MT[®] 220**

Formulation F-20-080-06 @ 20% N.V.

Maintenance Program: Suitable for low to medium maintenance programs with propane or electric machines and light to medium aggressive pads.

Syntran MT 220-based formulation F-20-080-06 provides a protective coating with 3 coats of application with 60° specular gloss value of < 45.

	100 Gallon Formula	
<i>Mix in Order Listed:</i>	<u>Pounds</u>	<u>Weight %</u>
Water	365.80	42.50
Biocide	Q.S.	Q.S.
Syntran[®] 4015 @ 30% N.V.	36.00	4.20
Premixed Plasticizers:		
Tributoxyethyl Phosphate	17.50	2.00
Diethylene Glycol Ethyl Ether (low gravity)	51.50	6.00
1% Zonyl FSN	7.20	0.80
Syntran MT[®] 220 @ 38% N.V.	325.00	37.80
Syntran[®] 6150 @ 40% N.V.	23.20	2.70
Syntran[®] PA-1445 @ 40% N.V.	15.40	1.80
Syntran[®] 1560 @ 25% N.V.	18.50	2.20
Defoamer	<u>Q.S.</u>	<u>Q.S.</u>
YIELD:	860.00	100.00%

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 80 / 10 / 10