

## Interpolymer offers two suggested formulations for Syntran<sup>®</sup> 1671 Concrete Sealer.

*(This is an interactive PDF file. Simply click on the links appropriate to the information you wish to view.)*

- Concrete Sealer with Urethane
- Concrete Sealer without Urethane

**FLOOR SEALER BASED ON SYNTRAN® 1671**

Formulation F-20-063-25 @ 25% N.V.

*Mix in Order Listed:*

	<u>Pounds</u>	<u>Weight %</u>
Water	261.10	30.30
Premix:		
Tributoxy Ethyl Phosphate	20.70	2.40
Diethylene Glycol Ethyl Ether	64.70	7.50
1% Active Zonyl FSA	7.80	0.90
Propylene Glycol	6.50	0.80
<b>Syntran® 1671 @ 40% N.V.</b>	<b>388.30</b>	<b>45.20</b>
Solucote 1080 @ 35% N.V.	110.90	12.90
YIELD:	860.00	100.00%

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 100 / 0 / 0

03/04

## CONCRETE SEALER BASED ON **SYNTRAN® 1671**

Formulation F-20-063-77 @ 20% N.V.

*Mix in Order Listed:*

	<u>Pounds</u>	<u>Weight %</u>
Water	408.50	47.50
Premix:		
Tributoxy Ethyl Phosphate	11.40	1.30
Diethylene Glycol Methyl Ether	41.40	4.80
1% Active Zonyl FSO	5.20	0.60
15-S-7	5.20	0.60
<b>Syntran® 1671 @ 40% N.V.</b>	<b>388.30</b>	<b>45.20</b>
YIELD:	<u>860.00</u>	<u>100.00%</u>

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 100 / 0 / 0

2005