

Interpolymer offers
two suggested formulations for
Megatran[®] 220.

(This is an interactive PDF file. Simply click on the links appropriate to the information you wish to view.)

- Floor Finish Formulation F-41-038-02 Based on Megatran 220
- *Recommended for North American use*
Matte Floor Finish Formulation F-20-080-06 Based on Megatran 220

FLOOR FINISH BASED ON **MEGATRAN[®] 220**

Formulation F-41-038-01 @ 25% N.V.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	277.61	32.28
Bactericide	Q.S.	Q.S.
Premixed:		
Tributoxyethyl Phosphate	26.39	3.07
Diethylene Glycol Ethyl Ether (low gravity)	52.78	6.14
1% Masurf FS230	6.28	0.73
Megatran 220 @ 38% N.V.	446.41	51.91
Syntran 6160 @ 35% N.V.	26.93	3.13
Syntran PA-1445 @ 40% N.V.	23.60	2.74
Defoamer	Q.S.	Q.S.
YIELD:	860.00	100.00%

pH: 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 90 / 0 / 10

2005

MATTE FLOOR FINISH BASED ON MEGATRAN[®] 220

Formulation F-20-080-06 @ 18% N.V.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	415.20	48.30
Syntran[®] 4015 @ 30% N.V.	32.40	3.80
Premix:		
Tributoxy Ethyl Phosphate	15.70	1.80
Diethylene Glycol Methyl Ether	46.30	5.40
1% Active Zonyl FSN	6.50	0.80
Megatran[®] 220 @ 38% N.V.	292.50	34.00
Syntran[®] 6150 @ 40% N.V.	20.80	2.40
Syntran[®] PA-1465 @ 40% N.V.	13.90	1.60
Syntran[®] 1560 @ 25% N.V.	16.70	1.90
YIELD:	860.00	100.00%

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 80 / 10 / 10