

**FLOOR FINISH BASED ON SYNTRAN® 1905**

Formulation F-20-019-05 @ 22% N.V.

*Mix in Order Listed:*

	<u>Pounds</u>	<u>Weight %</u>
Water	332.40	38.50
Premix:		
Tributoxy Ethyl Phosphate	20.30	2.40
Diethylene Glycol Ethyl Ether	30.40	3.50
1% Active Zonyl FSN	6.80	0.80
Texanol	5.60	0.70
Dipropylene Glycol Methyl Ether	11.30	1.30
<b>Syntran® 1905 @ 38% N.V.</b>	<b>373.20</b>	<b>43.40</b>
<b>Syntran® 6160 @ 35% N.V.</b>	<b>38.60</b>	<b>4.50</b>
<b>Syntran® PA-1445 @ 40% N.V.</b>	<b>21.10</b>	<b>2.50</b>
<b>Syntran® 1560 @ 25% N.V.</b>	<b>20.30</b>	<b>2.40</b>
<b>YIELD:</b>	<b>860.00</b>	<b>100.00%</b>

Polymer/Resin/Wax Ratio: 84 / 3 / 13