

# SYNTRAN<sup>®</sup> 1921

## Zinc free polymer for “Green” floor finishes

**SYNTRAN 1921** in **Formulation F-52-086-02** is suggested as a starting point green floor polish formulation for maintenance programs where occasional burnishing will be utilized. Formulation F-52-086-02 is zinc, ammonia and APE surfactant free, with a low VOC content.

### Formulation F-52-086-02 @ 20% N.V.

*Mix in Order Listed:*

	<u>Pounds</u>	<u>Weight %</u>
Water	405.60	47.20
Bactericide	q.s.	q.s.
Premixed Plasticizers:		
Tributoxyethyl Phosphate	28.70	3.30
Diethylene Glycol Ethyl Ether	38.20	4.40
1% Active Zonyl FSA	3.80	0.40
Tomadol 23-3	4.80	0.60
<b>SYNTRAN 1921 @ 38% N.V.</b>	339.50	39.50
<b>SYNTRAN 6160 @ 35% N.V.</b>	20.50	2.40
<b>SYNTRAN PA-1465 @ 38% N.V.</b>	18.90	2.20
Defoamer	q.s.	q.s.
YIELD:	860.00	100.00%

pH: 8.0± 0.2

Polymer/Resin/Wax Ratio: 90 / 0 / 10 4/2006