

FLOOR FINISH BASED ON **SYNTRAN MT[®] 240**

Formulation F-20-047-75 @ 25% N.V.

Syntran MT[®] 240-based formulation F-20-047-75 @ 25% non-volatile is formulated for application in areas where a durable high gloss appearance is desired. This formulation can sustain periodic high speed burnishing with a propane or electric machine using medium or aggressive pads.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	269.60	31.4
Bactericide	Q.S.	Q.S.
Premixed Plasticizers:		
Tributoxyethyl Phosphate	23.00	2.7
Diethylene Glycol Ethyl Ether (low gravity)	57.60	6.7
1% Active Zonyl FSA	7.70	0.9
Syntran MT[®] 240 @ 38% N.V.	449.30	52.2
Syntran[®] 6150 @ 40% N.V.	28.80	3.3
Syntran[®] PA-1445 @ 40% N.V.	24.00	2.8
Defoamer	Q.S.	Q.S.
YIELD:	860.00	100.00%

pH: 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 89 / 0 / 11