

CONCRETE SEALER BASED ON **SYNTRAN® 1671**

Formulation F-20-063-25 @ 25% N.V.

Syntran 1671 based urethane fortified formulation to provide excellent toughness and durability as a coating for interior concrete flooring.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	291.11	33.91
Premix:		
Tributoxy Ethyl Phosphate	20.11	2.34
Diethylene Glycol Ethyl Ether	50.26	5.84
1% Active Zonyl FSA	7.54	0.88
Propylene Glycol	6.30	0.70
Syntran® 1671 @ 40% N.V.	376.97	43.83
Solucote 1080 @ 35% N.V.	107.71	12.50
YIELD:	860.00	100.00%

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 100 / 0 / 0

03/04