

FLOOR FINISH BASED ON **SYNTRAN® 1501**

Formulation F-20-052-16 @ 25% N.V.

Mix in Order Listed:

	<u>Pounds</u>
Water	275.50
Premix:	
Tributoxy Ethyl Phosphate	24.20
Diethylene Glycol Ethyl Ether	47.00
1% Active Zonyl FSN	6.40
Syntran® 1248 @ 38% N.V.	431.60
AC325 @ 40% N.V.	28.60
Syntran® PA-1445 @ 40% N.V.	23.80
Syntran® 1501 @ 25% N.V.	22.90
YIELD:	860.00

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 86 / 3 / 11