

FLOOR SEALER BASED ON **SYNTRAN® 1076**

Formulation F-20-081-01

100 Gallon Formula @ 20% N.V.

Mix in Order Listed:

Water	408.4 Pounds
Bactericide	Q.S.
Premixed Plasticizers:	
Tributoxyethyl Phosphate	10.8
Diethylene Glycol Monomethyl Ether	32.3
1% Active Zonyl FSO Solution	5.4
Syntran® 1076 @ 40% N.V.	403.1
Defoamer	Q.S.
	YIELD: <u>860.0</u>
Adjust pH to 8.6 ± 0.2	