

FLOOR FINISH BASED ON **MEGATRAN[®] 240** & **SYNTRAN[®] PA-1465**

Formulation F-20-024-42 @ 25% N.V.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	272.60	31.70
Premix:		
Tributoxy Ethyl Phosphate	24.20	2.80
Diethylene Glycol Ethyl Ether	48.30	5.60
1% Active Zonyl FSA	7.60	0.90
Dripropylene Glycol Methyl Ether	6.40	0.70
Megatran[®] 240 @ 38% N.V.	436.60	50.80
Syntran[®] 6150 @ 40% N.V.	19.10	2.20
Syntran[®] PA-1465 @ 38% N.V.	45.20	5.30
YIELD:	860.00	100.00%

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 87 / 0 / 13