

CONCRETE SEALER BASED ON **SYNTRAN® 1671**

Formulation F-20-063-77 @ 20% N.V.

Syntran 1671, coating formulation F-20-063-77 offers excellent adhesion, appearance and durability to interior concrete floors.

Mix in Order Listed:

| | <u>Pounds</u> | <u>Weight %</u> |
|--------------------------------|---------------|-----------------|
| Water | 408.49 | 47.51 |
| Premix: | | |
| Tributoxy Ethyl Phosphate | 11.39 | 1.32 |
| Diethylene Glycol Methyl Ether | 41.42 | 4.82 |
| 1% Active Zonyl FSO | 5.18 | 0.60 |
| 15-S-7 | 5.20 | 0.60 |
| Syntran 1671 @ 40% N.V. | 388.32 | 45.15 |
| YIELD: | 860.00 | 100.00% |

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 100 / 0 / 0

2005