

**FLOOR FINISH BASED ON MEGATRAN<sup>®</sup> 240 & SYNTRAN<sup>®</sup> 6150**

Formulation F-20-047-22 @ 25% N.V.

*Mix in Order Listed:*

	<u>Pounds</u>	<u>Weight %</u>
Water	273.60	31.90
Premix:		
Tributoxy Ethyl Phosphate	21.90	2.50
Diethylene Glycol Ethyl Ether	51.50	6.00
1% Active Zonyl FSO	9.00	1.00
<b>Megatran<sup>®</sup> 240 @ 38% N.V.</b>	431.70	50.20
<b>Syntran<sup>®</sup> 6150 @ 40% N.V.</b>	48.20	5.60
<b>Syntran<sup>®</sup> PA-1445 @ 40% N.V.</b>	24.10	2.80
YIELD:	860.00	100.00%

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 85 / 0 / 15