

DRY BRITE FLOOR FINISH BASED ON ALL-ACRYLIC **SYNTRAN® A170**

Formulation F-17-032-20 @ 25% N.V.

Maintenance Program: Suitable for low to medium maintenance programs with propane or electric machines and light to medium aggressive pads.

100 Gallon @ 25% N.V.

	<u>Pounds</u>	<u>Weight %</u>
<i>Mix in Order Listed:</i>		
Water	265.40	30.90
Biocide	Q.S	Q.S.
<i>Premixed Plasticizers:</i>		
Tributoxyethyl Phosphate	24.20	2.80
Diethylene Glycol Ethyl Ether (low gravity)	50.90	5.90
1% Active Zonyl FSO	8.90	1.00
Texanol	10.20	1.20
Syntran® A170 @ 38% N.V.	441.70	51.40
Syntran 6150 @ 40% N.V.	28.60	3.30
Syntran PA-1465 @ 38% N.V.	30.10	3.50
Defoamer	Q.S.	Q.S.
YIELD:	860.00	100.00

pH: 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 88 / 0 / 6:6

Weight Per Gallon: 8.51