

DRY BRIGHT FLOOR FINISH BASED ON MEGATRAN® 240

Formulation F-41-25-01 @ 25% N.V.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	278.44	32.38
Bactericide	Q.S.	Q.S.
Premixed Plasticizers:		
Tributoxyethyl Phosphate	27.50	3.20
Diethylene Glycol Ethyl Ether (low gravity)	50.00	5.81
1% Active Zonyl FSO or 1% Masurf FS230	5.00	0.58
TXIB	6.25	0.73
MEGATRAN® 240 @ 38% N.V.	468.75	54.51
SYNTRAN® 6150 @ 40% N.V.	11.72	1.36
SYNTRAN® PA-1465 @ 38% N.V.	12.34	1.43
Defoamer	Q.S.	Q.S.
YIELD:	<u>860.00</u>	<u>100.00%</u>

pH: 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 95 / 0 / 5