

FLOOR POLISH BASED ON SYNTRAN® 1242

Formulation F-35-015-01 @ 20% N.V.

Floor polish

High Gloss
 Good Wear properties
 High Durability

Mix in Order Listed:

	<i>p.b.w</i>	
Tributoxyethyl Phosphate ⁽¹⁾	1.8	plasticizer
Diethylene Glycol Ethyl Ether ⁽²⁾	4.3	coalescent
Zonyl FSN 1% solution ⁽³⁾	1.0	leveling agent
Water	43.4	
SYNTRAN® 1242 @38% N.V.	40.9	polymer dispersion
SYNTRAN® WE1401 @35% N.V.	5.6	wax emulsion
SYNTRAN® 1560 @25% N.V.	2.9	alkali soluble resin
Degressal SD40 ⁽⁴⁾	0.1	defoamer
Bactericide		
Yield:	100.0	

Preparation:

Add all ingredients in listed order under good stirring, and stir 30 minutes. Adjust pH to 8.5 ± 0.2 and stir for another 30 minutes before filter and package.

Formulation Information:

Polymer/Resin/wax ratio : 85/4/11
 Solids : 20%
 pH : 8.5

- (1) Interpolymer
- (2) Dow
- (3) Dupont
- (4) BASF