

WOOD SANDING SEALER BASED ON **SYNTRAN® 6302**

Formulation F-43-048-01 25% N.V.

The **SYNTRAN 6302** sanding sealer formulation is designed to fill and seal wood pores completely before applying a topcoat. This **quick drying** sealer formulation **sands easily** to a smooth surface for even topcoating. Formulation F-43-048-01 should not be used in combination with topcoats based on **SYNTRAN 6130**.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	232.81	27.07
Citric acid	4.30	0.50
Dipropylene Glycol Methyl Ether	8.60	1.00
Syntran 6302 @ 35% N.V.	614.29	71.43
Bactericide	Q.S.	Q.S.
Defoamer	Q.S.	Q.S.
YIELD:	860.00	100.00%

pH: 5.2

Procedure

- Using good agitation add ingredients in the order listed.
- Mix until a homogenous solution results (20-30 minutes).

2004