

FLOOR FINISH BASED ON **MEGATRAN<sup>®</sup> 240 & SYNTRAN<sup>®</sup> PA-1445**

Formulation F-20-086-20 @ 25% N.V.

*Mix in Order Listed:*

	<u>Pounds</u>	<u>Weight %</u>
Water	268.30	31.20
Premix:		
Tributoxy Ethyl Phosphate	25.30	2.90
Diethylene Glycol Ethyl Ether	50.60	5.90
1% Active Zonyl FSA	6.30	0.70
Dripropylene Glycol Methyl Ether	12.60	1.50
<b>Megatran<sup>®</sup> 240 @ 38% N.V.</b>	459.00	53.40
<b>Syntran<sup>®</sup> PA-1445 @ 40% N.V.</b>	37.90	4.40
YIELD:	860.00	100.00%

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 92 / 0 / 8