

STONE AND MARBLE FINISH BASED ON SYNTRAN® 1671

Formulation F-41-037-04 @ 25% N.V.

Syntran 1671 formulation F-41-037-04 is designed to provide excellent adhesion and water resistance as a sealer for tile and stone surfaces.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	297.22	34.60
Bactericide	Q.S.	Q.S.
<i>Premixed Plasticizers:</i>		
Tributoxyethyl Phosphate	25.29	2.90
Diethylene Glycol Ethyl Ether	59.44	6.91
1% Active Masurf FS230	3.79	.44
SYNTRAN 1671 @ 40% N.V.	474.26	55.15
Defoamer	Q.S.	Q.S.
YIELD:	<u>860.00</u>	<u>100.00%</u>

pH: 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 100 / 0 / 0