

WOOD SANDING SEALER BASED ON **SYNTRAN® 6302**

Formulation F-43-013-01 25% N.V.

The **SYNTRAN 6302** sanding sealer formulation is designed to fill and seal wood pores completely before applying a topcoat. This **quick drying** sealer formulation **sands easily** to a smooth surface for even topcoating.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	230.90	26.90
Bactericide	Q.S.	Q.S.
Premixed Plasticizers:		
Tributoxyethyl Phosphate	6.90	0.80
Diethylene Glycol Ethyl Ether (low gravity)	27.70	3.20
Syntran® 6302 @ 35% N.V.	594.50	69.10
Defoamer	Q.S.	Q.S.
YIELD:	860.00	100.00%

pH: 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 100 / 0 / 0