

## FLOOR FINISH BASED ON SYNTRAN 1299

Formulation F-14-086-2

100 Gallon Formula @ 25% N.V.

*Mix in Order Listed:*

Water	270.2 Pounds
Bactericide	Q.S.
Premixed Plasticizers:	
Tributoxyethyl Phosphate	19.5
Diethylene Glycol Ethyl Ether – Low gravity	45.6
1% Active Zonyl FSA Solution	6.5
Ethylene Glycol Phenyl Ether	5.2
<b>Syntran 1299 @ 38% N.V.</b>	431.8
<b>Syntran PA-1465 @ 38% N.V.</b>	61.7
<b>Syntran 6150 W/E @ 40% N.V.</b>	19.5
Defoamer	Q.S.
	YIELD: <u>860.0</u>

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 84 / 0 / 16

8/04