

DRY BRITE FLOOR FINISH BASED ON MEGATRAN 260F

UNIQUE, PROPRIETARY FLUORO-ACRYLIC POLYMER TECHNOLOGY

Formulation F-20-018-62 @ 22% N.V.

MAINTENANCE PROGRAM: Recommended for low to medium maintenance programs with propane or electric machines and light to medium aggressive pads.

Recommended for Scrub and Recoat maintenance programs where extended time periods between recoat cycles are required.

Mix in Order Listed:

	<u>Pounds</u>	<u>Weight %</u>
Water	345.70	40.20
Biocide	Q.S.	Q.S.
Premixed Plasticizers:		
Tributoxyethyl Phosphate	21.30	2.50
Diethylene Glycol Ethyl Ether (low gravity)	48.10	5.60
1% Active Zonyl FSA	5.60	0.70
Megatran[®] 260F @ 38% N.V.	393.10	45.70
Syntran[®] 6150 @ 40% N.V.	25.20	2.90
Syntran[®] PA-1445 @ 40% N.V.	21.00	2.40
Defoamer	Q.S.	Q.S.
YIELD:	860.00	100.00%

PH: 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 89/ 0 / 11