

FLOOR FINISH BASED ON **SYNTRAN® 1560**

Formulation F-20-091-04 @ 19% N.V.

Mix in Order Listed:

	<u>Pounds</u>
Water	24.20
Premix:	
Tributoxy Ethyl Phosphate	1.30
Diethylene Glycol Methyl Ether	7.50
1% Active Zonyl FSA	0.50
Texanol	0.50
Caprolactam	1.60
Syntran® 1560 @ 25% N.V.	64.40
Defoamer	Q.S.
	<hr/>
YIELD:	860.00

Adjust pH to 8.6 ± 0.2

Polymer/Resin/Wax Ratio: 0 / 100 / 0