

FLOOR POLISH BASED ON SYNTRAN® 1285

Formulation F-35-006-01 @ 20% N.V.

Floor polish

High Gloss
 Good Wear properties
 High Durability

Mix in Order Listed:

p.b.w

| | | |
|--|-------|--------------------|
| Tributoxyethyl Phosphate ⁽¹⁾ | 2.4 | plasticizer |
| Diethylene Glycol Ethyl Ether ⁽²⁾ | 4.1 | coalescent |
| Zonyl FSP 1% solution ⁽³⁾ | 1.0 | leveling agent |
| Water | 47.8 | |
| SYNTRAN® 1285 @ 40% N.V. | 37.5 | polymer dispersion |
| SYNTRAN® WE1401 @ 35% N.V. | 3.7 | wax emulsion |
| SYNTRAN® PA1465 @ 38%N.V. | 3.4 | wax emulsion |
| Degressal SD40 ⁽⁴⁾ | 0.1 | defoamer |
| Bactericide | Q.S. | |
| Yield: | 100.0 | |

Preparation:

Add all ingredients in listed order under good stirring, and stir 30 minutes. Adjust pH to 8.5 ± 0.2 and stir for another 30 minutes before filter and package.

Formulation Information:

Polymer/Resin/wax ratio : 85/0/15
 Solids : 20%
 pH : 8.5

- (1) Interpolymer
- (2) Dow
- (3) Dupont
- (4) BASF